

FICHA DE DADOS DO PRODUTO

Sikalastic®-827 HT

Modified hot-melt adhesive

DESCRIÇÃO DO PRODUTO

Sikalastic®-827 HT is a modified, expanding copolymer, hot-melt pellet adhesive. It bonds mastic asphalt, stone mastic asphalt and asphalt concrete to Sika bridge deck waterproofing systems.

UTILIZAÇÕES

Sikalastic®-827 HT may only be used by experienced professionals.

The pellets are used for:

- Broadcasting onto wet Sikalastic®-8902 Broadcasting onto wet SikaCor® HM Mastic

CARACTERÍSTICAS / VANTAGENS

- Provides a bond between Sika spray applied waterproofing membrane and asphalt overlay
- Provides a mechanical key due to expansion when in contact with hot asphalt
- Develops good bond and shear strength performance

CERTIFICADOS / NORMAS

- Adhesive Layer in Waterproofing System ZTV-IN Part 7 Section 4, Sikalastic®-827 HT, kiwa, Test report No. P 8332-1-E
- Bridge Waterproofing System Sikalastic®-851, BBA, Certificate No. 15/H237, according BBA HAPAS guideline
- CE Marking and Declaration of Performance to ETA-18/1105, based on ETAG 033 Liquid applied bridge deck waterproofing kits

DADOS DO PRODUTO

Base química	Modified Ethyl-Vinyl-Acetate-Copolymer	
Fornecimento	25 kg bags Refer to current price list for packaging variations	
Tempo de armazenamento	24 months from date of production	
Armazenagem e conservação	Product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging.	
Massa volúmica	~20 kg/l, bulk density Values at +23 °C	(EN ISO 2811-1)

DADOS TÉCNICOS

Resistência química	Resistant to water, bitumen and de-icing salts
---------------------	--

INFORMAÇÃO SOBRE A APLICAÇÃO

FICHA DE DADOS DO PRODUTO

Sikalastic®-827 HT

Setembro 2021, VERSÃO 02.01

02070680210000001

Consumo	~0,70 kg/m ²
Temperatura ambiente	Refer to the individual Product Data Sheet of the tack coat system

VALOR BASE

Todos os dados técnicos referidos nesta Ficha de Produto são baseados em ensaios laboratoriais. Resultados obtidos noutras condições podem divergir dos apresentados, devido a circunstâncias que não podemos controlar.

OBSERVAÇÕES

- Do not broadcast Sikalastic®-827 HT onto the tack coat if the pot life is exceeded.
- The asphalt paving temperature must be a minimum +140 °C on concrete deck surfaces.
- The asphalt paving temperature must be a minimum +160 °C on steel deck surfaces.

ECOLOGIA, SAÚDE E SEGURANÇA

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

INSTRUÇÕES DE APLICAÇÃO

RESTRIÇÕES LOCAIS

Por favor, ter em atenção que o desempenho deste produto poderá variar ligeiramente de país para país, em função dos parâmetros regulamentares específicos de cada local. Por favor, consultar a Ficha de Produto para a descrição completa dos campos de aplicação.

NOTA LEGAL

A informação e em particular as recomendações relacionadas com aplicação e utilização final dos produtos Sika são fornecidas em boa fé e baseadas no conhecimento e experiência dos produtos sempre que devidamente armazenados, manuseados e aplicados em condições normais, de acordo com as recomendações da Sika. Na prática, as diferenças no estado dos materiais, das superfícies, e das condições de aplicação em obra, são de tal forma imprevisíveis que nenhuma garantia a respeito da comercialização ou aptidão para um fim em particular nem qualquer responsabilidade decorrente de qualquer relacionamento legal poderão ser inferidas desta informação, ou de qualquer recomendação por escrito, ou de qualquer outra recomendação dada. O produto deve ser ensaiado para aferir a adequabilidade do mesmo à aplicação e fins pretendidos. Os direitos de propriedade de terceiros deverão ser observados. Todas as encomendas aceites estão sujeitas às nossas condições de venda e de entrega vigentes. Os utilizadores deverão sempre consultar a versão mais recente da nossa Ficha de Produto específica do produto a que diz respeito, que será entregue sempre que solicitada.

SIKA MOÇAMBIQUE, LDA
Boane, Matola Rio, Parcela 3441
MOCAMBIQUE
Phone : + 25 821 730 367
[HTTPS://moz.sika.com/](https://moz.sika.com/)

FICHA DE DADOS DO PRODUTO
Sikalastic®-827 HT
Setembro 2021, VERSÃO 02.01
02070680210000001

Sikalastic-827HT-pt-MZ-(09-2021)-2-1.pdf